

ALTO SYN PGE

PRODUCT DATA SHEET

August 22, 2012

375 Stewart Road, Hanover Twp., PA 18706 | P: (570)822-1151 | F: (570)823-1910

GENERAL DESCRIPTION

ALTO SYN PGE is formulated to address the specific problems associated with conventional rotary screw and centrifugal compressor lubricants which is thermal degradation and deposit formation. The polyglycol/ester blend provides superior performance in the areas of oxidation resistance and deposit formation. ALTO SYN PGE eliminates the varnish, sludge and the frequent lubricant changes associated with petroleum oils.



Petroleum Service Company
375 Stewart Road, Hanover Twp., PA 18706
Phone: (570)822-1151 • Fax: (570)823-1910

August 22, 2012

375 Stewart Road, Hanover Twp., PA 18706 | P: (570)822-1151 | F: (570)823-1910

PRODUCT DATA SHEET

NOTE: The information in this publication is the result of careful testing in our laboratories, complemented by selected literature. It does not in any way constitute a guarantee, nor widely varying conditions of product use, which are beyond our control, it is strongly recommended that the product be tested for suit ability. Product typical this publication are current as of November 24, 2010.

Physical Properties

COMPRESSOR LUBRICANT

ALTO SYN PGE

SAE GRADE	32	46	10W-20
Viscosity @ 40°C, cSt	38.3	54.9	54.9
@ 100°C, cSt	7.30	9.32	9.32
@ 100°F, SUS	195	279	279
@ 210°F, SUS	50.6	57.7	57.7
Viscosity Index	158	153	153
Specific Gravity	0.9650	0.9652	0.9652
Density, lbs/gal	8.036	8.038	8.038
Pour Point, °F (°C)	-65 (-54)	-54 (-48)	-54 (-48)
Flash Point, °F (°C)	480 (249)	510 (266)	510 (266)
Autoignition Temp., °F (°C)	730 (388)	750 (399)	750 (399)
Conradson Carbon, % Residue	0.020	0.028	0.028
Rotary Bomb Oxidation Test, Min.	2300	2300	2300
Evaporation Loss Percentage, 22 hours @ 210°F	0.26	0.26	0.26


 Petroleum Service Company
 375 Stewart Road, Hanover Twp., PA 18706
 Phone: (570)822-1151 · Fax: (570)823-1910